



CNTFET biosensor design

Nicolas Champauzas

► **To cite this version:**

Nicolas Champauzas. CNTFET biosensor design. 21ème Journées Nationales du Réseau Doctoral en Micro-nanoélectronique (JNRDM), Jun 2019, Montpellier, France. lirmm-02363551

HAL Id: lirmm-02363551

<https://hal-lirmm.ccsd.cnrs.fr/lirmm-02363551>

Submitted on 14 Nov 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

CNTFET biosensor design

Nicolas Champauzas – LIRMM, University of Montpellier, CNRS, Montpellier, France

The thesis:


This research starts with a state of the art review on biosensing and applications. Then followed with the design of a structure using the advantages of carbon nanotubes (CNT) as a field effect transistor and as an interface with a biological field. Indeed CNTs are known to be very sensitive to their electrical environment and to chemical changes at close range [1]. Moreover, CNTs, thanks to their hexagonal carbon lattice, can be used as a substrate for organic molecules deposition; allowing the creation of a selective layer [2].

The target:

One of the main drags in cancer research is the ability to observe related biomarkers. We choose here, as a target, one of those biomarkers: the Cyclin dependent Kinase (CDK) complex CDK4/CyclinD. This enzyme is used as a proof of concept for monitoring the activity of the CDK family. Indeed, CDKs, also called *cell division cycle protein*, are responsible for the self-destruction of a tumour cell [3]. An uncontrolled increase in the activity of CDK4/CyclinD complex allows a defective cell to multiply. This enzyme is identified as a biomarker of skin cancers among others [4]. These enzymes use phosphorylation – giving or receiving electrically loaded PO_3 groups – as an activating/deactivating signal.

The sensor:

The designed architecture aims to a sensitive and selective sensor that would also be cheap to manufacture for measurement of CDK4/CyclinD activity. CNTs are placed by dielectrophoresis between facing combs as electrodes [5]. The contacts are then closed with a second layer of Au over the metal-contacting parts of the CNTs. The metal surfaces are insulated with PDMS allowing functionalisation of only the channel parts of the CNTs. Pbase – 1-pyrenebutanoic acid succinimidyl ester – is then used as a linker between the CNT sidewall and a polypeptide – substrate specific to CDK4/CyclinD – forming an ion-selective layer. The activity of CDK4/CyclinD is measured by the rate of presence of PO_3 ions. Indeed, the local changes in charge density can be observed through gate effect on the CNT as a transistor channel [6].



Biosensor functional decomposition and analogy to the CNTFET structure in design

- [1] Melendrez Armada, Daniel Alfonso, John Edward Proctor, Vijayaraghavan Aravind; *An introduction to graphene and carbon nanotubes*, 2017, CRC press
- [2] N. T. Tung, *Basic study on Peptide Aptamer-modified Single-Walled Carbon Nanotube Field-Effect Transistor (SWCNT FET) for biomolecule analysis*, JAIST Repository, 2016
- [3] G. Krauss, *Biochemistry of Signal Transduction*, vol. 2. 2001.
- [4] Camille Prével, Morgan Pellerano, Juan A. González-Vera, Pauline Henri, Laurent Meunier, Julien Vollaire, Véronique Josserand, May C. Morris, *Fluorescent peptide biosensor for monitoring CDK4/cyclin D kinase activity in melanoma cell extracts, mouse xenografts and skin biopsies*, *Biosensors Bioelectronics*, vol. 85, pp. 371–380, 2016.
- [5] Z. Bin Zhang, X. J. Liu, E. E. B. Campbell, and S. L. Zhang, *Alternating current dielectrophoresis of carbon nanotubes*, *J. Appl. Phys.*, vol. 98, no. 5, pp. 5–8, 2005.
- [6] J. Appenzeller, J. Knoch, R. Martel, V. Derycke, S. J. Wind, and P. Avouris, *Carbon nanotube electronics*, vol. 1, no. 4. 2002.